



SYLENTMITE

The fastest expanding mortar system

PLEASE READ BEFORE USE

SYLENTMITE may have a similar appearance or texture to other products you have used in the past - Please be aware that IT MUST BE MIXED ACCORDING TO THE ENCLOSED DIRECTIONS ONLY

PLEASE BE SURE TO FOLLOW ALL INSTRUCTIONS ENCLOSED AND USE ACCORDINGLY

- Hole diameter **MUST** be minimum 38mm, 50mm may return better results.
- Drill the holes, clean out, and allow to cool **BEFORE** filling with Sylentmite.
- Mix Sylentmite as directed only - Mixed product should **NEVER** be able to be poured.
- After an amount of product is put into each hole (say 1/3), tamp down firmly and evenly using a Broom handle / Dowel. Repeat this regularly until the hole is completely filled - Be **SURE** not to leave any air pockets. Each hole **MUST** be filled completely - **NEVER** return to a part filled hole and add new product on top - **THIS WILL CAUSE A BLOW OUT.**
- **KEEP YOUR PPE IN PLACE - EVEN AFTER THE HOLES ARE FILLED**
- **STAND WELL BACK - NEVER LOOK INSIDE THE HOLES.**
- Whilst cracks **CAN** start appearing from as little as 15 minutes, please note that depending on the rock type and ambient temperatures, this may not be achievable.

Need further information? Contact your local dealer or
e-mail : support@sylentmite.com

www.sylentmite.com